

REPORT



We create chemistry

BASF Nederland BV
PO Box 287
NL-5280 AG Boxtel

BASF Nederland BV
Hemelrijk 11-13
NL-5281 PS Boxtel

Phone +31 (0) 411 615 615
Fax +31 (0) 411 615 616
Internet: www.pu.basf.eu/nl
E-mail pu-nl@basf.com

Structure formula	Chemicals	Elastocoat C 6335/101
C ₃ H ₆ O	Acetone	C
NH ₃ (1%)	Ammonia (1%)	R
NH ₄ OH (50%)	Ammoniumhydroxide (50%)	RC
C ₂ H ₄ O ₂ (5%)	Vinegar / water (5%)	R
C ₂ H ₄ O ₂ (10%)	Acetic acid (10%)	R
C ₂ H ₄ O ₂ (100%)	Acetic acid (100%)	C
C ₆ H ₆	Benzene	C
KOH (10%)	Potassium Hydroxide (10%)	R
KOH (20%)	Potassium Hydroxide (20%)	R, Ver
Cl + H ₂ O	Chlorinated water	C
Mixture	Diesel Fuel	RC
P ₃ H ₃ O ₄ (10%)	Phosphoric acid (10%)	R
P ₃ H ₃ O ₄ (50%)	Phosphoric acid (50%)	NR
Mixture	Hydraulic oil	RC
HF (10%)	Hydrofluoric acid (10%)	NR
C ₃ H ₈ O	Isopropyl alcohol	RC
C ₄ H ₈ O	MEK	RC
C ₃ H ₈ O ₃	Lactic acid	RC
CH ₄ O	Methanol	C
Cl ₂ CH ₂	Methylene chloride	C
Mixture	Motor oil	R
NaCl (10%)	NaCl (10%)	R
NaOH (50%)	NaOH (50%)	R, Ver
NaOH (pH 12)	NaOH (pH 12)	R
CHNaO ₃	Sodium bicarbonate	R
NaOCl (10%)	Sodium hypochlorite (10%)	R
HNO ₃ (20%)	Nitric acid (20%)	NR
Mixture	Spirit	RC
C ₇ H ₈	Toluene	C
H ₂ O	Water	R
HCl (37%)	Hydrochloric acid (37%)	R
H ₂ SO ₄ (10%)	Sulphuric acid (10%)	R
H ₂ SO ₄ (>50%)	Sulphuric acid (>50%)	RC

R	Recommended, little or no visible damage
RC	Recommended conditional, some effect, swelling, discoloration
C	Conditional, was down within 1 hour of spillage to avoid effects
NR	Not recommended
Ver	Discoloration

This guide is for general information only, therefore no rights can be derived from this document.

BASF NEDERLAND BV

® = registered trade mark of BASF

The data contained in this document as well as advice or other support services are based on our current knowledge and experience and are provided according to our best knowledge. In view of many factors that may affect processing and application of our products, this data does not relieve processors from carrying out their own investigations and tests, particularly with regards to the suitability of the goods supplied for the processes and purposes they intend to use them for; neither does this data imply any guarantee of certain properties, or the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, measured values etc. given herein may change without prior notice and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Nederland B.V.
PO box 287
5180 AG Boxtel
The Netherlands

Tel: +31 (0) 411 615 615
Fax: +31 (0) 411 615 616
Mail: pu-nl@basf.com
Internet: www.pu.basf.eu/nl